

ECISS  
**EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDISATION**  
**COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER**  
**EUROPÄISCHES KOMITEE FÜR EISEN- UND STAHLNORMUNG**  
 EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM – CRM)  
**CERTIFICATE OF CHEMICAL ANALYSIS**

**EURONORM – CRM No. 097-2 High Purity Iron**

**LABORATORY MEANS (4 Values)**  
 mass content in %

Line No	Si	Mn	P	S	Cr	Mo	Ni	As	B	Co	Cu	N	Sn	V	W
1	0.00234	0.0108	—	0.00156	0.0196	—	—	0.00238	0.00004	0.0129	—	—	0.00030	0.00006	—
2	0.00245	0.0109	0.00414	0.00156	0.0198	0.00267	0.0206	0.00252	0.00005	0.0130	0.00729	0.00243	0.00032	0.00007	0.00311
3	0.00250	0.0111	0.00500	0.00160	0.0201	0.00348	0.0213	0.00253	0.00007	0.0131	0.00736	0.00273	0.00033	0.00007	0.00355
4	0.00251	0.0113	0.00507	0.00168	0.0202	0.00348	0.0229	0.00260	0.00008	0.0132	0.00738	0.00280	0.00035	0.00008	0.00367
5	0.00253	0.0114	0.00512	0.00170	0.0205	0.00350	0.0230	0.00263	0.00009	0.0132	0.00759	0.00283	0.00035	0.00009	0.00379
6	0.00260	0.0115	0.00513	0.00173	0.0206	0.00353	0.0232	0.00265	0.00010	0.0135	0.00769	0.00286	0.00038	0.00009	0.00380
7	0.00260	0.0115	0.00518	0.00173	0.0207	0.00358	0.0232	0.00265	0.00010	0.0136	0.00769	0.00288	0.00039	0.00010	0.00382
8	0.00263	0.0117	0.00519	0.00175	0.0207	0.00363	0.0237	0.00267	0.00012	0.0136	0.00770	0.00288	0.00040	—	0.00384
9	0.00268	0.0118	0.00522	0.00183	0.0207	0.00370	0.0239	0.00273	0.00013	0.0136	0.00776	0.00288	0.00040	0.00010	0.00385
10	0.00275	0.0119	0.00523	0.00185	0.0209	0.00370	0.0240	0.00273	0.00013	0.0137	0.00778	0.00289	0.00040	0.00010	0.00391
11	0.00283	0.0119	0.00523	0.00190	0.0210	0.00375	0.0240	0.00277	0.00015	0.0138	0.00779	0.00290	0.00040	0.00011	0.00398
12	0.00307	0.0120	0.00530	0.00195	0.0212	0.00375	0.0241	0.00284	0.00017	0.0138	0.00780	0.00303	0.00043	0.00013	0.00400
13	0.00322	0.0120	0.00531	0.00198	0.0212	0.00378	0.0242	0.00288	0.00017	0.0139	0.00781	0.00305	0.00050	0.00018	—
14	0.00323	0.0121	0.00547	0.00199	0.0215	0.00381	0.0242	0.00291	0.00018	0.0139	0.00783	0.00308	0.00051	0.00020	0.00400
15	0.00326	0.0121	0.00548	0.00200	0.0216	0.00382	0.0242	0.00292	0.00020	0.0140	0.00790	0.00314	0.00052	—	0.00408
16	0.00330	0.0121	0.00551	0.00207	0.0216	0.00383	0.0243	0.00292	0.00020	0.0140	0.00793	0.00325	0.00053	0.00010	0.00410
17	0.00333	0.0121	0.00559	0.00216	0.0216	0.00383	0.0244	0.00292	0.00020	0.0141	0.00794	0.00343	0.00053	0.00010	0.00410
18	0.00350	0.0122	0.00568	0.00218	0.0218	0.00383	0.0245	0.00313	0.00020	0.0141	0.00808	0.00343	0.00054	0.00010	0.00413
19	—	0.0122	0.00585	0.00220	0.0220	0.00384	0.0245	0.00315	0.00020	0.0142	0.00815	0.00343	0.00059	0.00010	—
20	—	0.0122	0.00593	0.00220	0.0220	0.00386	0.0246	0.00319	0.00020	0.0142	0.00818	0.00343	0.00059	0.00010	—
21	—	0.0124	0.00610	0.00220	0.0220	0.00387	0.0246	0.00320	0.00020	0.0142	0.00820	0.00343	0.00059	0.00010	—
22	—	0.0125	0.00623	0.00221	0.0221	0.00400	0.0247	0.00320	0.00020	0.0146	0.00835	0.00343	0.00059	0.00010	—
23	—	0.0126	0.00623	0.00222	0.0222	0.00405	0.0255	0.00319	0.00020	0.0147	0.00838	0.00343	0.00059	0.00010	—
24	—	0.0127	0.00623	0.00224	0.0224	0.00405	0.0255	0.00319	0.00020	0.0148	0.00844	0.00343	0.00059	0.00010	—
25	—	0.0127	0.00623	0.00225	0.0225	0.00405	0.0257	0.00319	0.00020	0.0153	0.00853	0.00343	0.00059	0.00010	—
26	—	0.0133	0.00623	0.00235	0.0235	0.00405	0.0268	0.00319	0.00020	0.0153	0.00867	0.00343	0.00059	0.00010	—
27	—	0.0133	0.00623	0.00235	0.0235	0.00405	0.0268	0.00319	0.00020	0.0153	0.00867	0.00343	0.00059	0.00010	—
<b>M<sub>M</sub></b>	<b>0.00285</b>	<b>0.0120</b>	<b>0.00538</b>	<b>0.00181</b>	<b>0.0213</b>	<b>0.00370</b>	<b>0.0241</b>	<b>0.00281</b>	<b>0.00012</b>	<b>0.0139</b>	<b>0.00793</b>	<b>0.00294</b>	<b>0.00043</b>	<b>0.00011</b>	<b>0.00386</b>
<b>S<sub>M</sub></b>	0.00037	0.0007	0.00045	0.00017	0.0010	0.00028	0.0013	0.00024	0.00005	0.0006	0.00037	0.00023	0.00009	0.00005	0.00026
<b>S<sub>W</sub></b>	0.00033	0.0003	0.00024	0.00014	0.0003	0.00012	0.0004	0.00011	0.00002	0.0003	0.00011	0.00012	0.00004	0.00002	0.00013

Line No	Sb	Ta	Zn	C	Al <sub>tot</sub>	Nb	Pb	Ti	Zr	Bi	Ca	Mg	O	Ga
1	0.00010	0.00007	0.00003	0.00005	0.0001	0.0007	<0.0001	0.00005	<0.0001	<0.0001	<0.0001	<0.0001	0.0040	0.00006
2	0.00011	0.00008	0.00007	<0.0001	0.0002	0.0007	<0.0001	0.00037	<0.0001	<0.0001	0.00002	<0.0001	0.0043	0.00032
3	0.00011	0.00009	0.00007	<0.0002	0.0002	0.0007	0.00001	0.00038	0.00001	<0.0001	0.00007	0.00004	0.0050	0.00047
4	0.00012	0.00014	0.00008	0.00024	0.0002	0.0008	0.00001	0.00040	0.00001	0.00001	0.00010	0.00005	0.0052	—
5	0.00012	0.00016	0.00011	0.00025	0.0002	0.0008	0.00001	0.00046	0.00002	<0.0002	<0.0002	0.00005	0.0055	—
6	0.00012	0.00017	0.00014	0.00037	0.0003	0.0008	0.00001	0.00054	0.00004	<0.0002	<0.0002	<0.0010	0.0057	—
7	0.00012	0.00019	0.00015	<0.0005	<0.0004	0.0008	0.00002	0.00058	0.00005	0.00002	<0.0002	0.00010	—	—
8	0.00013	0.00019	0.00020	0.00050	0.0004	0.0009	<0.0005	0.00062	0.00005	0.00005	0.00040	0.00013	—	—
9	0.00013	0.00019	0.00024	0.00076	0.0006	0.0009	<0.0001	0.00065	<0.0001	0.00005	<0.0005	<0.0002	—	—
10	0.00014	0.00022	0.00024	0.00181	0.0007	0.0009	<0.0001	0.00076	≤0.0001	0.00008	<0.0005	0.00020	—	—
11	0.00016	—	0.00025	0.00195	<0.0001	0.0010	<0.0001	0.00078	0.00010	<0.0001	0.00058	0.00023	—	—
12	—	—	—	0.00203	0.0010	0.0012	0.00011	0.00082	0.00010	<0.0001	—	0.00029	—	—
13	—	—	—	0.00208	0.0011	0.0012	0.00018	0.00085	0.00010	0.00010	0.00034	0.00034	—	—
14	—	—	—	0.00243	0.0012	0.0012	0.00031	0.00090	0.00014	0.00080	—	<0.0005	—	—
15	—	—	—	—	0.0013	0.0015	0.00073	0.00095	0.00015	—	—	<0.0006	—	—
16	—	—	—	—	0.0013	0.0016	<0.0008	0.00096	<0.0005	—	—	—	—	—
17	—	—	—	—	0.0014	0.0016	<0.001	0.00097	<0.0006	—	—	—	—	—
18	—	—	—	—	0.0015	0.0016	0.00100	0.00101	<0.0016	—	—	—	—	—
19	—	—	—	—	0.0017	0.0017	0.00100	0.00110	—	—	—	—	—	—
20	—	—	—	—	0.0019	0.0019	0.00100	0.00115	—	—	—	—	—	—
21	—	—	—	—	—	—	—	0.00145	—	—	—	—	—	—
<b>M<sub>M</sub></b>	<b>0.00012</b>	<b>0.00015</b>	<b>0.00014</b>											
<b>S<sub>M</sub></b>	0.00002	0.00006	0.00008											
<b>S<sub>W</sub></b>	0.00001	0.00002	0.00004											

**Additional Information:** Ag: <0.0001%, Al (sol): <0.0004%, 0.0010%, Cd: <0.0001%, Ge: 0.00043%, 0.00066%, Se: <0.0001%, Te: <0.0001%

M<sub>M</sub>: Mean of the intralaboratory means, S<sub>M</sub>: Standard deviation of the intralaboratory means, S<sub>W</sub>: Intralaboratory standard deviation

The laboratory mean values have been examined statistically to eliminate outlying values. Where a "—" appears in the table it indicates that an outlying value has been eliminated by either the Cochran or Grubbs Test. Values reported as "less than" values by the participating laboratories have not been taken into account in the statistical calculations.

Values given in italics are for information only.

**CERTIFIED VALUES**

Mass content in %

	Si	Mn	P	S	Cr	Mo	Ni	As	B
<b>M<sub>M</sub></b>	<b>0.00285</b>	<b>0.0120</b>	<b>0.00538</b>	<b>0.00181</b>	<b>0.0213</b>	<b>0.00370</b>	<b>0.0241</b>	<b>0.00281</b>	<b>0.00012</b>
C(95%)	0.00019	0.0003	0.00021	0.00009	0.0004	0.00013	0.0006	0.00011	0.00003
	Co	Cu	N	Sn	V	W	Sb	Ta	Zn
<b>M<sub>M</sub></b>	<b>0.0139</b>	<b>0.00793</b>	<b>0.00294</b>	<b>0.00043</b>	<b>0.00011</b>	<b>0.00386</b>	<b>0.00012</b>	<b>0.00015</b>	<b>0.00014</b>
C(95%)	0.0003	0.00016	0.00013	0.00005	0.00003	0.00014	0.00002	0.00004	0.00006

The half-width confidence interval C(95%) =  $\frac{t \times S_M}{\sqrt{n}}$  where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 sections 6.1 and 10.5.2

**This certified reference material was prepared in accordance with the recommendations set out in ISO Guides 30 – 35 and issued by:**

**BUREAU OF ANALYSED SAMPLES LIMITED**

Newham Hall, Middlesbrough, England TS8 9EA

On behalf of: The Iron and Steel Nomenclature Co-ordinating Committee (COCOR) of the ECISS, after approval by all the participating laboratories and all the producing organizations. (France – IRSID/CTIF, Germany – Iron and Steel CRM Working Group: Stahlinstitut VDEH, BAM Bundesanstalt für Materialforschung und –prüfung & MPI für Eisenforschung, Nordic Countries – Nordic CRM Working Group, UK – BAS Ltd.)



4004

**EURONORM – CRM No. 097-2**  
**METHODS USED**

Element	Line Number	Methods
<b>Si</b>	1-4-5-6-7-10-12-14-15-16-18	Inductively Coupled Plasma-Optical Emission Spectrometry
	2-3-8-11-17	Spectrophotometry, molybdenum blue, without extraction
	9	Glow Discharge-Mass Spectrometry
	13	Inductively Coupled Plasma-Mass Spectrometry
<b>Mn</b>	1-3-4-5-6-10-11-14-15-16-17-19-21-22-23-24-25	Inductively Coupled Plasma-Optical Emission Spectrometry
	2-18-20-26-27	Inductively Coupled Plasma-Mass Spectrometry
	7-9	Spectrophotometry, periodate oxidation
	8	Glow Discharge-Mass Spectrometry
	12-13	Flame Atomic Absorption Spectrometry
<b>P</b>	2-3-4-5-6-7-8-10-12-13-14-19-20	Inductively Coupled Plasma-Optical Emission Spectrometry
	9-11-16-21-22	Spectrophotometry, phosphovanadomolybdate, extraction
	15	Spectrophotometry, molybdenum blue, without extraction
	17-18	Inductively Coupled Plasma-Mass Spectrometry
<b>S</b>	1-2-3-4-5-6-9-10-12-13-14-15-16	Combustion, infrared absorption
	7	Gravimetry as BaSO <sub>4</sub> , without separation
	8	Glow Discharge-Mass Spectrometry
	11	Combustion, acidimetric titration, absorption in H <sub>2</sub> O <sub>2</sub>
<b>Cr</b>	1-2-3-5-6-9-10-11-13-14-15-16-17-18-19-20-21-22-23	Inductively Coupled Plasma-Optical Emission Spectrometry
	4	Glow Discharge-Mass Spectrometry
	7-8-12-24-25	Inductively Coupled Plasma-Mass Spectrometry
<b>Mo</b>	2	Spectrophotometry, thiocyanate in presence of Sn (II), extraction
	3-7-9-14-15-22	Inductively Coupled Plasma-Mass Spectrometry
	4-5-6-8-10-11-12-13-16-17-19-20-21-23	Inductively Coupled Plasma-Optical Emission Spectrometry
	18	Glow Discharge-Mass Spectrometry
<b>Ni</b>	2-4-5-6-7-9-10-11-13-14-15-16-17-18-19-22-23-25	Inductively Coupled Plasma-Optical Emission Spectrometry
	3-8-21-26	Inductively Coupled Plasma-Mass Spectrometry
	12-24	Flame Atomic Absorption Spectrometry
	20	Glow Discharge-Mass Spectrometry
<b>As</b>	1-3	Spectrophotometry, diethyldithiocarbamate, separation as arsine
	2-4-5-6-8-10-13-15-19-21	Inductively Coupled Plasma-Optical Emission Spectrometry
	7-9-11-14-17-18	Inductively Coupled Plasma-Mass Spectrometry
	12	Electrothermal Atomic Absorption Spectrometry
	16	Flame Atomic Absorption Spectrometry, evolution as arsine
20	Flame Atomic Absorption Spectrometry	
<b>B</b>	1-4-5-6-12	Inductively Coupled Plasma-Mass Spectrometry
	2-7-8-9-11	Inductively Coupled Plasma-Optical Emission Spectrometry
	3-10-13-14-15	Spectrophotometry, curcumin
<b>Co</b>	1-2-3-4-5-6-7-8-9-12-13-14-16-19-20-21-23-24-25	Inductively Coupled Plasma-Optical Emission Spectrometry
	10-15-17-18-22	Inductively Coupled Plasma-Mass Spectrometry
	11	Glow Discharge-Mass Spectrometry
<b>Cu</b>	2-6-10-16	Inductively Coupled Plasma-Mass Spectrometry
	3-4-5-7-8-9-11-12-13-14-15-17-19-20-22-23-24-25-26	Inductively Coupled Plasma-Optical Emission Spectrometry
	18-21	Flame Atomic Absorption Spectrometry
<b>N</b>	2-3-4-5-6-8-9-10-11-12-14-15-16-17	Thermal Conductivity, decomposition in graphite crucible
	7	Acidimetric titration after distillation, visual end point
	13	Spectrophotometry, Nessler reagent, distillation
<b>Sn</b>	1-2-4-7-8-10-17	Inductively Coupled Plasma-Mass Spectrometry
	3	Electrothermal Atomic Absorption Spectrometry
	5-9-11-12-13-16-18-19	Inductively Coupled Plasma-Optical Emission Spectrometry
	6	Glow Discharge-Mass Spectrometry
<b>V</b>	14-15	Flame Atomic Absorption Spectrometry
	1-2-4-6-7	Inductively Coupled Plasma-Mass Spectrometry
	3	Glow Discharge-Mass Spectrometry
<b>W</b>	5-9-10-11-12-13-14	Inductively Coupled Plasma-Optical Emission Spectrometry
	2-3-4-5-6-7-8-9-11-12-17	Inductively Coupled Plasma-Optical Emission Spectrometry
	10	Glow Discharge-Mass Spectrometry
	14-15-16-18	Inductively Coupled Plasma-Mass Spectrometry

**EURONORM – CRM No. 097-2  
METHODS USED**

Element	Line Number	Methods
<b>Sb</b>	1-2-3-7-9-10-11	Inductively Coupled Plasma-Mass Spectrometry
	4	Electrothermal Atomic Absorption Spectrometry
	5	Flame Atomic Absorption Spectrometry, hydride generation
	6	Flame Atomic Absorption Spectrometry
	8	Glow Discharge-Mass Spectrometry
<b>Ta</b>	1-2-3-4-6-8-10	Inductively Coupled Plasma-Mass Spectrometry
	5-7-9	Inductively Coupled Plasma-Optical Emission Spectrometry
<b>Zn</b>	1-3-4-9-11	Inductively Coupled Plasma-Mass Spectrometry
	2-6-10	Flame Atomic Absorption Spectrometry
	5-7-8	Inductively Coupled Plasma-Optical Emission Spectrometry
<b>C</b>	1-2-3-4-5-6-7-8-9-10-11-12	Combustion, infrared absorption
	13	Combustion, non-aqueous titration after absorption in organic solvent
	14	Combustion, coulometric titration
<b>Al<sub>Tot</sub></b>	1-10-18	Inductively Coupled Plasma-Mass Spectrometry
	2-4-5-6-7-8-9-11-12-13-14-15-16-17	Inductively Coupled Plasma-Optical Emission Spectrometry
	3	Electrothermal Atomic Absorption Spectrometry
<b>Nb</b>	1-3-5-7-11-20	Inductively Coupled Plasma-Mass Spectrometry
	2-4-6-8-9-10-12-13-14-15-16-17-18	Inductively Coupled Plasma-Optical Emission Spectrometry
	19	Glow Discharge-Mass Spectrometry
<b>Pb</b>	1-4-5-6-9-10-11	Inductively Coupled Plasma-Mass Spectrometry
	2	Glow Discharge-Mass Spectrometry
	3-12-15	Flame Atomic Absorption Spectrometry
	7-8	Electrothermal Atomic Absorption Spectrometry
	13-14-16-17-18-19	Inductively Coupled Plasma-Optical Emission Spectrometry
<b>Ti</b>	1-5-9-20-21	Inductively Coupled Plasma-Mass Spectrometry
	2-3-4-6-7-8-10-11-12-13-14-15-16-18-19	Inductively Coupled Plasma-Optical Emission Spectrometry
	17	Glow Discharge-Mass Spectrometry
<b>Zr</b>	1	Glow Discharge-Mass Spectrometry
	2-3-5-7-8-9-15	Inductively Coupled Plasma-Mass Spectrometry
	4-6-10-11-12-13-14-16-17-18	Inductively Coupled Plasma-Optical Emission Spectrometry
<b>Bi</b>	1-3-7-11-12	Inductively Coupled Plasma-Mass Spectrometry
	2	Glow Discharge-Mass Spectrometry
	4-8	Flame Atomic Absorption Spectrometry, hydride generation
	5	Flame Atomic Absorption Spectrometry
	6-9	Electrothermal Atomic Absorption Spectrometry
	10-13-14	Inductively Coupled Plasma-Optical Emission Spectrometry
<b>Ca</b>	1	Glow Discharge-Mass Spectrometry
	2-4-8-9-10-11	Inductively Coupled Plasma-Optical Emission Spectrometry
	3-6-7	Flame Atomic Absorption Spectrometry
	5	Inductively Coupled Plasma-Mass Spectrometry
<b>Mg</b>	1	Glow Discharge-Mass Spectrometry
	2-7-11-13	Inductively Coupled Plasma-Mass Spectrometry
	3-5-10-12-14-15	Inductively Coupled Plasma-Optical Emission Spectrometry
	4-6-8-9	Flame Atomic Absorption Spectrometry
<b>O</b>	1-2-3-6	Infrared absorption measurement, reduction fusion under helium
	4-5	Infrared absorption measurement, reduction fusion under vacuum
<b>Ga</b>	1	Inductively Coupled Plasma-Optical Emission Spectrometry
	2	Inductively Coupled Plasma-Mass Spectrometry
	3	Glow Discharge-Mass Spectrometry

**PARTICIPATING LABORATORIES**

Acerinox S.A., Algeciras, Spain	IncoTest, Hereford, UK
AG der Dillinger Hüttenwerke, Dillingen, Germany	Pattinson & Stead (2005) Ltd, Middlesbrough, UK
Alcoa Howmet, Exeter, UK	Ridsdale & Co Ltd., Middlesbrough, UK
ALS Scandinavia, Luleå, Sweden	Rautaruukki Oyj, Raahe, Finland
ArcelorMittal Dunkerque, Dunkerque, France	Saarstahl AG, Völklingen, Germany
ArcelorMittal Florange, Florange, France	Sandvik Materials Technology, Sandviken, Sweden
ArcelorMittal Research, Maizières-lès-Metz, France	Shiva Technologies, Tournefeuille, France
ATI-Allvac Ltd, Sheffield, UK	Swerea Kimab, Stockholm, Sweden
Aubert & Duval, Les Ancizes, France	Tata Steel IJmuiden, IJmuiden, The Netherlands
BAM Bundesanstalt für Materialforschung und -prüfung, Berlin, Germany	Tata Steel, Port Talbot, UK
Böhler Edelstahl GmbH, Kapfenberg, Austria	Tata Steel, Stocksbridge, UK
CTIF, Sèvres, France	Tata Steel, Scunthorpe, UK
DCNS, La Montagne, France	ThyssenKrupp Steel Europe AG, Duisburg, Germany
Heraeus Materials Technology GmbH, Hanau, Germany	Thyssen Krupp VDM GmbH, Werdohl, Germany
Höganäs AB, Höganäs, Sweden	voestalpine Stahl Linz GmbH, Linz, Austria
IFW, Dresden, Germany	

**EURONORM – CRM No. 097-2**  
**DESCRIPTION OF THE SAMPLE**

The sample consists of chips passing a nominal 1700µm aperture sieve from which the fines passing a nominal 250µm sieve has been removed. It is supplied in bottles containing 100g, ref ECRM 097-2(C). It is also supplied in the form of 38mm dia. discs, ref ECRM 097-2(D)

**INTENDED USE & STABILITY**

ECRM 097-2 (C) is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the contents should become discoloured (e.g. oxidised) by atmospheric contamination they should be discarded.

ECRM 097-2 (D) is intended for establishing and checking the calibration of Optical Emission and X-Ray Spectrometers for the analysis of similar materials. The "as received" working surface of the sample should be lished before use to remove any protective coating. It will remain stable provided that it is not subjected to excessive heat (e.g. during preparation of the working surface).

**TRACEABILITY**

**The traceability of ECRM 097-2 has been established in accordance with principles of ISO Guides 30 – 35 and the International Vocabulary of Basic and General Terms In Metrology.**

The characterisation of this material has been achieved by inter-laboratory study, each laboratory using the method of their choice, details of which are given above. These methods are either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds. Most methods used were either international or national standard methods or methods which are technically equivalent.

**FURTHER INFORMATION**

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMs) and the use of the statistical information given on this certificate, please refer either to the producer of this Certified Reference Material or to Technical Reports CEN/TR 10317:2009 and CEN/TR 10350:2009, both of which are available from the national standards body in your country. (In the UK this is the BSI, 389 Chiswick High Road, London W4 4AL).

Further information and advice on this or other Certified Reference Materials or Reference Materials produced by Bureau of Analysed Samples Ltd. may be obtained from the address below.

Pour disposer d'informations sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM-MRC) ainsi que sur l'utilisation des informations statistiques données sur ce certificat, se reporter soit au producteur de ce Matériau de Référence Certifié, soit aux Rapports Techniques CEN/TR 10317:2009 et CEN/TR 10350:2009. On peut se procurer ces deux documents auprès des organismes nationaux de normalisation. (Pour la France: AFNOR, 11 Avenue Francis de Pressensé, 93571 – St Denis la Plaine Cedex).

D'autres informations et avis au sujet de ce Matériau de Référence Certifié, ou de tout autre Matériau de Référence Certifié ou Matériau de Référence produits par le Bureau of Analysed Samples Ltd., peuvent être demandés en contactant l'adresse figurant dans le bas de ce Certificat.

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Europäischen Zertifizierten Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendungen der in diesem Zertifikat enthaltenen statistischen Daten sind erhältlich beim Hersteller dieses zertifizierten Referenzmaterials, oder sie finden sich in den CEN-Reports CEN/TR 10317:2009 und CEN/TR 10350:2009, beide zu beziehen durch die nationalen Normenorganisationen. (In Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstraße 4-10, 10787 Berlin).

Weitere Informationen und Hinweise zu diesem oder anderen durch Bureau of Analysed Samples Ltd. hergestellten zertifizierten Referenzmaterialien oder Referenzmaterialien können unter der unten angegebenen Adresse erhalten werden.

För information angående tillverkning, certifiering och anskaffning av dessa europeiska certifierade referensmaterial (EURONORM CRM) och för användning av statistisk information, som angivits i detta certifikat, refereras antingen till producenten av detta certifierade referensmaterial eller till Teknisk Rapport CEN/TR 10317:2009 och CEN/TR 10350:2009 som kan erhållas från den nationella standardiseringsorganisationen. (Sverige: SIS, S:t Paulsgatan 6, SE-118 80 Stockholm, Finland: SFS, PL. 116, FIN-002 41, Helsingfors, Danmark: DS, Kollegievej 6, DK-Charlottenlund 2920, Norge: NSF, Drammensveien, 145 A, Postboks 353 Skøyen, NO-0213 Oslo, Island: STRI, Holtgardar, IS-104 Reykjavik).

Ytterligare information och rådfrågan om detta eller andra Certifierade Referensmaterial/Referensmaterial, producerade av Bureau of Analysed Samples Ltd. kan erhållas från angiven adress enligt nedan.

NEWHAM HALL, NEWBY,  
MIDDLESBROUGH, ENGLAND, TS8 9EA  
Email: [enquiries@basrid.co.uk](mailto:enquiries@basrid.co.uk)  
Website: [www.basrid.co.uk](http://www.basrid.co.uk)

For BUREAU OF ANALYSED SAMPLES LTD.

R P MEERES,  
MANAGING DIRECTOR