

Standard Reference Elastomers (SRE): BAM-E014

Elastomer ISO 13226 SRE-FKM/2X / ISO 6072 FKM 2

1. Scope and field application

These SREs are representative of FKM materials such as are used, e. g., for parts in contact with petroleum products in the mechanical-engineering and automotive sector.

They are used for the characterization of service fluids such as mineral oils, fuels, lubricants, hydraulic fluids, coolants and refrigerants with regard to their effect on vulcanized fluoropolymer rubbers.

The changes in mass, volume, hardness, tensile strength and elongation at break of the SRE when in contact with the service fluid under specified conditions may be included as supplementary data in specifications for the fluid concerned.

<u>2.</u>	Formulation of the rubber mixture		Parts by mass
		Vinylidene fluoride-hexafluoropropylene copolymer (Tecnoflon N 935)	100,0
	C)	Calcium hydroxide (Fluorox E)	2,0
		Magnesium oxide (Elastomag 170)	3,0
	e)	Carbon black N 990 (Servacarb MT)	25,0
		Organic phosphonium salt (Tecnoflon FOR M2)	1,45
	h)	Bisphenol AF (Tecnoflon FOR M1)	2,76
		Conditions of vulcanization: 180 °C, 10 min	

3.1 Specifications, ISO 13226

 a) Density according to ISO 2781 b) Hardness according to ISO 48-2 c) Tensile strength according to ISO 37 d) Elongation at break according to ISO 37 e) Increase in mass in liquid C, as in ISO 1817, CO SC, 24 b 	(1,83 - 1,87) g/cm ³ (67 - 73) IRHD (12 - 18) MPad) (250 - 330) % (6 - 9) %
as in ISO 1817, 60 °C, 24 h	

3.2 Specifications, ISO 6072

b) c) d) e)	Density according to ISO 2781 Hardness according to ISO 48-2 Tensile strength according to ISO 37 Elongation at break according to ISO 37 Compression set according to ISO 815-1 Increase in mass in liquid E, as in ISO 1817 23 °C, 22 h	(1,82 - 1,88) g/cm ³ (67 - 73) IRHD 12 MPa min. 250 % min. 15 % max. (1 - 5) %
	23 °C, 22 h	

4. Dimensions

2 mm x 181 mm x 181 mm

<u>5. Storage</u>

Cool, dry, protected from light and kept in a protective cover (e.g. polyethylen bag) completely closed.

6. Guarantee

If used properly: 1 year.

7. Identification

The standard reference elastomer sheet is labelled indicating the producer (BAM), the year of production, the standard, the type of SRE and serial number.

The SRE is produced, certified and supplied by

Bundesanstalt für Materialforschung und -prüfung (BAM)

<u>Division 7.5</u> Unter den Eichen 87 12205 Berlin

Tel.: +49 (0) 30 8104-3230, -1749 Fax: +49 (0) 30 8104-1707 Email: <u>crm-elastomer@bam.de</u> Webshop: <u>https://www.webshop.bam.de/</u>