

date

The Reference Material (BAM-E016) delivered by BAM, Division 7.5 "Technical Properties of Polymeric Materials", is prepared for test purposes and tested in accordance with DIN EN ISO/IEC 17025:2005.

The properties of the rubber sheet **ISO 6072 NBR 2** correspond with the requirements given in ISO 6072 (\*).

The manufactured rubber reference plate is labelled (identification) as follows:

BAM (producer)
ISO 6072 (standard)
NBR 2 (type of elastomer)
BAM-E016 (product number)
XXXX (identification number)
19 (year of production)

Measurement results: determined from samples taken from a single standard plate from the charge mixture employed to produce plate number xx to xx.

	Requirements	Results	Standard Uncertainties
Density according to ISO 2781	(1,16 - 1,20) g/cm <sup>3</sup>	1,xx g/cm³	± 0,007 g/cm <sup>3</sup>
Hardness according to ISO 48-2 (micro-test)	(67 - 73) IRHD	x9 IRHD	± 2,6 IRHD
Tensile strength according to ISO 37	15 MPa min.	1x,5 MPa	± 2,0 MPa
Elongation at break according to ISO 37	300 % min.	3x1 %	± 46 %
Compression set according to ISO 815-1 (100 °C, 22 h)	20 % max.	1x %	± 1,2 %
Increase in mass in liquid B for fuels, as in ISO 1817; 23 °C, 22 h	(18 - 28) %	x %	± 1,0 %

The listed values for measurement uncertainties have a confidence level of 95 % (coverage factor=1,96). Measurement uncertainties are determined from the combination of measurement error and the standard deviation of the measurement results, resulting from inherent batch fluctuations.

(\*) - material charges are manufactured according to the given standard. Within these limitations slight deviations from the recommended requirements, as clearly listed in the illustrated results table, may occur.

by order

## Bundesanstalt für Materialforschung und -prüfung (BAM)

Dietmar Schulze; Quality Manager Division 7.5 Unter den Eichen 87 12205 Berlin Federal Republic of Germany

Tel.: +49 30 8104-3340 Fax: +49 30 8104-1707 Email: <u>crm-elastomer@bam.de</u>

Webshop: <a href="https://www.webshop.bam.de/">https://www.webshop.bam.de/</a>